

REPLACED BY
ART 34 AMDTClaims

1. A silicon holding vessel comprising a silicon composite thermet sprayed coating comprising metal silicon, silicon nitride and silicon oxide on at least a part of the interior wall of the silicon holding vessel.
2. A vessel according to claim 1, **characterized in that** the silicon composite thermet sprayed coating is formed by spraying a silicon composite thermet material made by adding metal silicon as a bonding material to a mixture of Si_3N_4 and SiO_2 .
3. A vessel according to claim 1 or 2, **characterized in that** the silicon composite thermet sprayed coating has a mixing ratio of metal silicon (X): silicon nitride (Y): silicon oxide (Z) of X:Y:Z = 20-50: 77-30: 3-20.
4. A vessel according to claim 1 or 2, **characterized in that** the silicon holding vessel is made from a material comprising silicon oxide, boron nitride and/or graphite.
5. A vessel according to claim 4, wherein the silicon oxide (SiO_2) is densified or sintered fused silica.
6. A vessel according to claim 1, **characterized in that** the coating has a thickness of 20-500 μm , preferably of 50-300 μm .
7. A method of producing a silicon holding vessel, which comprises spraying a silicon composite thermet material consisting of metal silicon, silicon nitride and silicon oxide on the interior wall of a silicon holding vessel, thereby forming a silicon composite thermet sprayed coating.
8. A method according to claim 7, wherein the silicon holding vessel is made from a material comprising silicon oxide, boron nitride and/or graphite, preferably densified or sintered fused silica.
9. A method according to claim 7, wherein the silicon thermet sprayed coating has a mixing ratio of metal silicon (X): silicon nitride (Y): silicon oxide (Z) of X:Y:Z = 20-50: 77-30: 3-20.